



Pacific Ceramics, Inc.

## Garnets

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant $\epsilon'$	Loss Tangent $\tan\delta_\epsilon$ ( $\times 10^{-4}$ )	Resonance Linewidth $\Delta H @ 3dB$ (oe)	Curie Temperature $T_C$ ( $^\circ C$ )
---------	--	---------------------------------------	--	--	---

---

### Holmium Doped for High RF Power Applications Yttrium Iron Garnet

39-1780H	1780	14.9	$\leq 1$	50	280
----------	------	------	----------	----	-----