



Pacific Ceramics, Inc.

Lithium Ferrites

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant ϵ'	Loss Tangent $\tan\delta_\epsilon$ ($\times 10^{-4}$)	Resonance Linewidth ΔH @3dB (oe)	Curie Temperature T_C ($^{\circ}C$)	Coercive Force H_C (oe)	Remanent Induction B_r (gauss)
---------	--	---------------------------------------	--	---	--	------------------------------------	---

Type 2 – Wide Temperature Performance, Square Hysteresis Loop

3-3402	3500	15.0	≤ 10	≤ 550	620	1.75	2700
3-3202	3200	15.2	≤ 5	≤ 525	600	1.75	2500
3-2902	2900	15.3	≤ 10	≤ 480	590	1.75	2240
3-2202	2200	16.1	≤ 10	≤ 500	500	1.75	1650
3-2002	2000	16.1	≤ 10	≤ 480	490	1.75	1570
3-1602	1600	16.8	≤ 10	≤ 480	425	1.75	1220
3-1202	1200	17.1	≤ 10	≤ 480	390	1.75	930
3-1002	1000	17.1	≤ 10	≤ 480	370	1.75	750